



## TECHNICAL DATA

### DESCRIPTION

Total thickness	EN ISO 24346 ( EN 428 )	mm	2.0mm
Wear layer thickness	EN ISO 24340 ( EN 429 )	mm	2.0mm
Weight	EN ISO 23997 ( EN 430 )	g/m <sup>2</sup>	3000 g/m <sup>2</sup>
Roll width	EN ISO 24341 ( EN 426 )	cm	200cm
Roll length	EN ISO 24341 ( EN 426 )	m	20m

### CLASSIFICATION

Classification	EN ISO 10874 ( EN 685 )	class	34-43
Fire rating	EN 13 501-1	class	Class Bfl-S1
	ASTM E648	class	Class1
	GB 8624-2012	class	GB 8624 B1
Toxic testing	GB 18586-2001	--	Good
Static electrical propensity	EN 1815	kv	<2
	EN 1081	Ω	≤10 <sup>9</sup>
Slip resistance dry	EN 13893	--	≥0.3
Slip resistance wet	DIN 51130	--	R9

### PERFORMANCE

Abrasion group	EN 660-2	Group	T
Type Binder content	EN ISO 10581	type	I
Dimensional stability	EN ISO 23999 ( EN 434 )	%	≤0.40
Residual indentation	EN ISO 24343-1 ( EN 433 )	mm	0.03
Thermal resistance	EN 12667	W(m.K)	0.01 m <sup>2</sup>
Colour fastness	EN ISO 105 - B02	degree	≥6
Chemical resistance	EN ISO 26987 ( EN 423 )	--	Good
Castor wheel test	ISO 4918 ( EN 425 )	--	Suitable
Impact sound reduction	EN ISO 717/2	dB	Approx +4
Flexibility	ISO 24344 ( EN 435 )	--	Excellent
Anti-bacterial and fungicidal	ISO 22196	--	Does not favour growth
Surface treatment			PUR
TVOC Emission	ISO 16000-6	µg/m <sup>3</sup>	<10 after 28 days
Underfloor heating		°C	Suitable max. 27 °C
Certification		Floorscore®	Floorscore®

